



Harbinger Focus Sport Floor

Harbinger Focus Non-Vulcanized Sport Floor				
	9mm Square Cut (Glue Down) 48" x 72" – 24 Sq.Ft. per mat		9mm Interlock (Loose Lay) 46.82" x 70.23" – 22.83 Sq.Ft. per mat	
	Per Mat	Per Sq.Ft.	Per Mat	Per Sq.Ft.
Grey / Grey				
Blue / Grey				
Black				
Black Skate Formula* Designed specifically for high skate traffic areas				
Grey/Grey Skate Formula* Designed specifically for high skate traffic areas				

*Skate Formula is produced to order & must be ordered in full block multiples.

45 lbs/mat | 50 mats/pallet – custom thicknesses & colours are available.

Tel: 604-324-8819

Updated: 06/01/2024

www.bayresourcegroup.ca

\$45 Pallet Fee, Freight & Taxes Not Included

Focus Sport Floor is a high-quality, durable rubber flooring designed to withstand the toughest conditions, whether its skates, ski boots, rolling loads, dropped weights, or rough equipment edges, we have you covered. Focus is non-porous, which minimizes clean up, odors and maintenance resulting in a better looking, longer lasting floor.

Features & Benefits

- Made in British Columbia
- Odorless, Certified for Indoor Air Quality
- Floor Score Certified
- Impact Absorbing
- Noise and Vibration Reducing
- Easy to Clean and Maintain
- Non-Porous
- Heavy Duty Dense Material
- Great Traction - Wet or Dry
- 5 Year Limited Warranty

Great For

- Ice Arenas
- CrossFit Gyms
- Dugouts
- Fitness Centers
- Ski Resorts





Harbinger Focus Sport Floor

TEST RESULTS

Description	Test Method	Result
Force Reduction	ASTM F2772	11.3%, Class 1
Ball Rebound		98.5% Passes
Surface Finish Effect		104 BPV Passes
Vertical Deflection/Deformation		0.6 mm Class B
Deformation	ASTM F2157	0.6 mm
Static Load Limit	ASTM F970	0.005 Inch @ 250 psi
Hardness	ASTM D2240	73 Shore A
Dimensional Stability/Curling Properties	ASTM F2199	Length: -0.010" per 12 inches Width: -0.019" per 12 inches
Flexibility	ASTM F137	Passes - 6mm Mandrel
Force Reduction	ASTM F2569	11.3%, Class 1
Slip Resistance	-	Average COF: Dry = 0.83
Breaking Load & Elongation	ASTM D412	Breaking load: 115.89 Lbs. Elongation: 137.02% Tensile: 479.9 lbs/sq. inch
Breaking Load and Elongation (Tensile Strength)		Breaking load: 51.98 lbs Elongation: 135.575 Tensile: 422.6 lbs/sq. in
Breaking Load and Elongation (Tensile Strength)		Breaking load: 51.51 lbs Elongation: 143.34% Tensile: 418.8 lbs/sq. in
Tensile/Elongation	-	Tensile: 650 PSI Elongation: 166%
Taber Abrasion	ASTM D4060	0.20 Grams (0.19%) loss
Taber Abrasion		0.47 Grams (0.89%) loss
Abrasion Resistance of Organic Coatings by the Taber Abraser		Weight loss: 0.55 grams (1.07%)

SUSTAINABILITY

Certification Attribute	Standard	3 rd Party Certification
Low-Emitting Material	CDPH/EHLB v1.2-2017 (California Section 01350)	#SCS-FS-02144
LEED Scorecard	MR2.2, MR4, MR5, EQ4.1, EQ4.3, ID1.1	-
Environmental Product Declaration (EPD)	-	SCS-EPD-03589
Health Product Declaration (HPD)	-	SCS-HPD-06698

Performance	Standard	Requirement	Performance vs. Requirement
TVOC Range	CDPH/EHLB v1.2-2017 (California Section 01350)	<0.5 mg/m ³	Pass
Low Emitting Adhesives	SCAQMD Rule #1168	Less than 50 g/L	Pass, 37 g/L
Recycled Content	90.33% Post-Consumer, 0.0% Post-Industrial, 90.33% Total Recycled Content		